

THERMOPLASTIC RESIN PELLET AND POLYESTER MOLDING PREPARED THEREFROM

Patent number: JP10316765
Publication date: 1998-12-02
Inventor: YUKI KIWAMU; MATSUDA TSUNETOSHI;
YOSHIMURA MASAHICO
Applicant: UNITIKA LTD
Classification:
- international: C08J3/22; C08L67/02
- european:
Application number: JP19970126694 19970516
Priority number(s): JP19970126694 19970516

Abstract of JP10316765

PROBLEM TO BE SOLVED: To obtain thermoplastic resin pellets which forms a reduced amt. of a cyclic oligomer when molten by using a thermoplastic resin containing a phosphoric-acid-derived-hydroxyl-containing P compound selected among a phosphoric acid comprising a P atom having a specified oxidation number, a phosphate or a phosphoric ester. **SOLUTION:** 2-10 wt.% phosphoric-acid-derived hydroxyl-containing P compound selected among a phosphoric acid, a phosphate and a phosphoric ester is added to a thermoplastic resin having an intrinsic viscosity of 0.5-2.0, and the mixture is melt-kneaded to prepare master pellets. Next, the master pellets are mixed with a thermoplastic pellets in a specified ratio, and the mixture is extruded at 250-270 deg.C and stretched at a draw ratio of 1.5-3.5 and a temperature of 80-110 deg.C to obtain a molding. The phosphorus compound comprises a P atom with an oxidation number of V and is a compound selected among orthophosphoric acid, metaphosphoric acid, polymetaphosphoric acid, polyphosphoric acid and salts and esters thereof and has phosphoric-acid-derived hydroxyl groups.

Data supplied from the esp@cenet database - Worldwide